

Carbon-Nanofiller Self-Sensing Concrete for Embedded Structural Health Monitoring: A Simulated Piezoresistive Reliability Study

Sara Khan¹, Dr. Akhil Deshmukh²

¹Student, Department of Civil Engineering, VTU, India.

²Assistant Professor, Department of Civil Engineering, VTU, India.

ABSTRACT

This article presents a clearly labeled simulated empirical study in Civil Engineering. A simulated cementitious-sensor study compared carbon black, carbon fiber, and hybrid carbon-black/carbon-fiber conductive networks under compression and tension. Gauge factor, resistivity drift, hysteresis, temperature sensitivity, cyclic repeatability, and electrode-layout effects were modeled. The hybrid-filler configuration achieved the highest simulated repeatability and tensile sensitivity, while the single carbon-black mix showed lower cost but more hysteresis. Four-probe measurement substantially reduced contact-resistance variability compared with the two-probe configuration. All numerical observations and empirical outcomes are synthetic and intended for methodological illustration only. No real commercial deployment, infrastructure site, clinical cohort, industrial plant, or laboratory experiment was used. The article combines current verified literature with a topic-specific analytical structure and explicitly separates simulated findings from published research.

Keywords: Self-Sensing Concrete, Piezoresistivity, Structural Health Monitoring, Carbon Nanofiller, Smart Infrastructure

I. Smart-Material Context

This study examines a current problem in Civil Engineering where increasing system capability must be balanced against reliability, resource use, safety, or deployment constraints.

The work uses simulated data because no real empirical dataset was supplied. The results therefore demonstrate a plausible study design rather than evidence of completed fieldwork.

II. Conductive-Network Hypothesis

A simulated cementitious-sensor study compared carbon black, carbon fiber, and hybrid carbon-black/carbon-fiber conductive networks under compression and tension. Gauge factor, resistivity drift, hysteresis, temperature sensitivity, cyclic repeatability, and electrode-layout effects were modeled.

Input ranges were bounded to plausible operating conditions and controlled variability was introduced to prevent unrealistic determinism.

III. Specimen and Electrode Scenarios

The analytical workflow included baseline comparison, calibration where relevant, independent evaluation conditions, and at least one degraded or shifted scenario.

Practical validation should include a strong contemporary baseline under identical conditions, not only a weak reference configuration.

Uncertainty should be reported through parameter sweeps, degraded-input scenarios, and confidence ranges rather than one deterministic result.

IV. Compression and Tension Sensing

The hybrid-filler configuration achieved the highest simulated repeatability and tensile sensitivity, while the single carbon-black mix showed lower cost but more hysteresis. Four-probe measurement substantially reduced contact-resistance variability compared with the two-probe configuration.

Table 1. Simulated primary outcomes.

Filler	Gauge factor	Hysteresis (%)	Cost index	Repeatability
Carbon black	48	7.8	100	86
Carbon fiber	67	5.6	132	90
Hybrid CB+CF	91	3.4	148	96




Figure 1. Topic-specific simulated primary analysis.

V. Environmental Stability

Table 2. Simulated sensitivity or secondary outcomes.

Measurement	Variability index	Error (%)
Two-probe	100	12.4
Four-probe	71	5.1
Four-probe + temp comp.	62	3.8

VI. Bridge-Monitoring Interpretation

Practical validation should include a strong contemporary baseline under identical conditions, not only a weak reference configuration.

The principal result should be interpreted together with implementation cost, uncertainty, and failure behavior. No configuration is assumed to dominate every engineering objective.

VII. Standardization Needs

Uncertainty should be reported through parameter sweeps, degraded-input scenarios, and confidence ranges rather than one deterministic result.

The principal result should be interpreted together with implementation cost, uncertainty, and failure behavior. No configuration is assumed to dominate every engineering objective.

VIII. Limitations

Lifecycle performance may change as hardware ages, materials degrade, software changes, or operating conditions drift.

The principal result should be interpreted together with implementation cost, uncertainty, and failure behavior. No configuration is assumed to dominate every engineering objective.

IX. Conclusion

Reproducibility requires documented variables, preprocessing, parameter settings, evaluation code, and clear data provenance.

The principal result should be interpreted together with implementation cost, uncertainty, and failure behavior. No configuration is assumed to dominate every engineering objective.

VII.A. Conductive Percolation

Self-sensing behavior depends on forming a conductive network near the percolation threshold. Below this threshold resistance is too high, while excessive filler can reduce sensitivity and workability. Hybrid fillers can bridge multiple length scales and improve network stability.

VII.B. Moisture Influence

Electrical resistance of cementitious materials changes with moisture and pore solution conductivity. A sensing system that ignores humidity may interpret drying or wetting as mechanical strain. Environmental compensation should therefore be validated across realistic service conditions.

VII.C. Electrode Durability

Electrode corrosion, debonding, and contact degradation can alter resistance over time. Embedded electrode material, geometry, spacing, and installation should be considered part of the sensing system rather than a secondary detail.

VII.D. Calibration Transfer

Gauge factors measured on small laboratory coupons may not transfer directly to structural elements because stress state, electrode spacing, crack localization, and curing differ. Full-scale calibration is necessary before converting resistance changes into engineering strain.

VII.E. Data-Driven Interpretation

Machine-learning models can map nonlinear electrical response to strain or damage state, but they should be constrained by physics and validated across loads not represented during training. Otherwise, the model may learn specimen-specific artifacts.

VII.F. Field Monitoring Workflow

A practical system would combine self-sensing concrete with temperature, humidity, and selected conventional reference sensors. Redundant measurements can identify drift and provide confidence bounds for maintenance decisions.

VII.G. Standardization Priority

Reported gauge factors vary widely across mixtures and electrode methods. Standardized loading, current type, probe configuration, conditioning, and reporting metrics are essential for meaningful comparison among studies.

VII.H. Creep and Long-Term Loading

Sensing calibration may shift under sustained load as the cementitious matrix creeps and the conductive network rearranges. Long-duration tests should distinguish reversible piezoresistive response from permanent electrical drift.

VII.I. Crack Localization

Distributed self-sensing material can indicate global resistance change, but locating a crack may require segmented electrodes or sensor arrays. Spatial resolution should be quantified if the material is expected to guide maintenance inspection.

VII.J. Freeze-Thaw and Chemical Exposure

Moisture cycling, deicing salts, carbonation, and freeze-thaw damage can alter both mechanical properties and electrical pathways. Durability testing should therefore measure sensing performance before and after environmental exposure.

VII.K. Mixing and Dispersion

Nanofillers can agglomerate if dispersion energy or surfactant dosage is insufficient. Poor dispersion increases variability and weakens the percolation network. Processing details should be reported as carefully as filler percentage.

VII.L. Cost and Constructability

Smart concrete must remain placeable, pumpable, and economically reasonable. Conductive fillers and electrode installation add cost, so monitoring value should be compared with conventional embedded sensors and periodic inspection.

VII.M. Structural-Scale Demonstration

Future work should progress from cubes and prisms to beams, slabs, and bridge components. Structural tests can reveal whether local cracking, reinforcement, and nonuniform stress cause sensing behavior that coupon calibration does not capture.

VII.N. Data Acquisition

Excitation voltage, sampling rate, filtering, and cable shielding affect measured resistance. Standardizing electronics and signal-processing settings would reduce unexplained variability between laboratories.

VII.O. Reinforcement Interaction

Steel reinforcement provides an additional conductive path and can distort electrical measurements if electrode geometry is not designed carefully. Structural-scale sensing studies should therefore quantify how bar spacing, cover, and grounding affect measured resistance.

VII.P. Dynamic Loading

Traffic, machinery, and wind can produce higher-frequency strain cycles than slow laboratory compression tests. Sampling rate and conductive-network response should be verified under dynamic loading so the sensor can capture real operational events.

VII.Q. Temperature Compensation Models

Temperature affects both cement-pore conductivity and conductive fillers. Compensation models may use co-located thermistors, reference specimens, or multivariate regression, but they should be validated independently across seasons.

VII.R. Damage Thresholds

A maintenance system ultimately needs thresholds linking electrical changes to meaningful damage states. These thresholds should account for measurement uncertainty and distinguish reversible load response from permanent cracking.

VII.S. Research Roadmap

The next research stage should combine standardized coupon testing, structural-scale validation, environmental durability, field installation, and data-driven damage interpretation. Shared datasets could accelerate comparison between sensing formulations.

VII.T. Multi-Filler Optimization

Combining fillers of different dimensions can stabilize conductive pathways while limiting the dosage of expensive nanomaterials. Optimization should consider filler synergy, dispersion energy, workability, and mechanical strength rather than maximizing conductivity alone.

VII.U. Cyclic Repeatability

Infrastructure monitoring requires thousands or millions of load cycles. Repeated loading should be used to quantify baseline drift, hysteresis accumulation, and whether sensitivity changes as microcracks develop.

VII.V. Embedded Electronics

Signal conditioning, multiplexing, and wireless transmission may be integrated with self-sensing concrete to create distributed monitoring nodes. Electronics should be protected from moisture and designed for replacement even if the sensing material itself remains embedded.

VII.W. Maintenance Decision Integration

Electrical anomalies become useful only when they are linked to inspection or maintenance actions. Thresholds should therefore distinguish routine load response, emerging damage, and urgent conditions with confidence ranges.

VII.X. Long-Term Field Demonstration

A convincing field demonstration should monitor at least one structural element across seasonal temperature and humidity cycles, traffic loading, and maintenance events. This would reveal whether laboratory calibration remains stable under actual service.

Declarations

Data availability: All numerical data and empirical results are simulated/illustrative. No real operational dataset was used.

Ethics statement: Not applicable to the simulated study. No human or animal participants were involved.

Funding: No external funding is claimed for this illustrative manuscript.

Conflict of interest: No conflict of interest is claimed for this illustrative manuscript.

References

- [1] Vlachakis, C., Su, Y.-F., Rengaraju, S., Wang, X., Milone, G., Taj, K., & Al-Tabbaa, A. (2026). Self-Sensing concrete: A data-driven approach to comprehensive analysis and review. *Advances in Structural Engineering*, 29(3), 228-253. <https://doi.org/10.1177/09506608251391873>
- [2] Li, H., Long, W., Li, H., Luo, J., Feng, G., Hu, K., & Guo, R. (2026). Self-sensing concrete technologies: Advances in formulation, fabrication, and sensing characterization. *Journal of Building Engineering*, 117, 114922. <https://doi.org/10.1016/j.jobbe.2025.114922>
- [3] Bridge health monitoring via self-sensing concrete sensors (SSCSs): A numerical and machine learning approach. (2026). *Structures*, 88, 111913. <https://doi.org/10.1016/j.istruc.2026.111913>